

TechResin® 2096

TechResin® 2096 is a high density, narrow molecular weight distribution polyethylene copolymer intended for general purpose injection molding and extrusion applications requiring a glossy surface finish and reasonably good impact strength and rigidity. It is characterized by a high melt index which allows easy processing of medium to thin-walled articles. This material meets the Food and Drug Administration requirements of 21 CFR 177.1520.

Typical Properties¹

	Values English Units	SI Units	ASTM Method
Resin			
Density		0.9530 g/cc	D4883
Melt Index 190 C/2.16 kg		20 g/10 min	D1238
Compression Molded Sample			
Tensile Strength (2 in/min)	4,000 psi	27.6 MPa	D638
@Yield	3,880 psi	26.7 MPa	
@Break			
Elongation (2 in/min)			D638
@Yield	9.1 %	9.1 %	
@Break	232%	232 %	
Flexural Modulus			D790A
Tangent Method	178,900 psi	1,227 MPa	
Notched Izod Impact Strength	0.53 ft-lbf/in	2.77 kJ/m ²	D256
Hardness			D2240
(Shore D)	66	66	
Vicat Softening Point	257 F	125 C	D1525
Brittleness Temperature	<-94 F	<-70 C	D746
Heat Deflection Temperature			D648
@66 psi (455 kPa)	162 F	72 C	
Environmental Stress Crack Resistance			D1693
Condition B, 100% Igepal, F50 (hrs.)	1.8	1.8	

¹ Typical properties will vary and are not to be used for specification purposes.

MDT does not guarantee reproduction of these results. This is not a Certificate of Analysis and the customer is responsible for testing and confirming the Material Properties before making commercial use of the product to ensure that the product is fit for the intended application and that the product can be used, and any waste material disposed of, safely, properly, and legally based on the customer's or other's circumstances. Determination of the suitability and fitness of the product for any particular application is the sole responsibility of the purchaser of the product. This information is solely intended for informational purposes. This material confirmation relates solely to the product listed above and not as incorporated in any product or used in any process. Material Difference Technology makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose. The customer or other user of the product assumes all risk and liability arising out of the use of the product, whether used alone or in combination with other materials. The presence absence or lack of information herein with respect to any particular international, national, federal, state or local law, statute, regulation, order or rule should not be construed to mean that product is regulated under, complies with or is exempt from such international, national, federal state or local law, statute, regulation, order or rule.