

TechResin[®] 1402E2

Linear Low Density Polyethylene (LLDPE) Resin Butene Copolymer for Film Extrusion Applications

TechResin[®] 1402E2 is a general-purpose film grade linear low density made using gas-phase technology. TechResin[®] 1402E2 exhibits excellent toughness and strength when drawn down to thin gauges in blown and cast film applications.

TechResin[®] 1402E2 meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

Suggested Applications:

Blending Resin	Industrial Liners
Industrial Packaging	Garment Bags
Co-Extrusion	

Nominal Physical Properties:

PROPERTY**	ASTM TEST METHOD	UNIT	VALUE
Density	D1505	g/cc	0.919
Melt Index, Condition E, 190°C/2.16 kg	D1238	g/10 min.	2.0
Dart Impact	D1709	g/mil.	65
Tear Strength	D1922	g/mil.	110/570*
Tensile Strength at Break	D882	psi.	3,900/2,700*
Elongation	D882	%	600/800*
Gloss, 45°	D523		40
Haze	D1003	%	35

* MD / TD

Available in the following additive packages:

Additive	1402B	1402E2
Antiblock (ppm)	None	7000
Slip (ppm)	None	1350
Special	-	Additives talc based

Note: Film Properties based on 25 Micron blown film produced with a 2.5:1 Blow Up Ratio. Actual film properties may vary depending on operating conditions and additive packages. Film properties are not intended to be used as specifications.

Published 08/01/04, Revised 01/11/16

MDT does not guarantee reproduction of these results. This is not a Certificate of Analysis and the customer is responsible for testing and confirming the Material Properties before making commercial use of the product to ensure that the product is fit for the intended application and that the product can be used, and any waste material disposed of, safely, properly, and legally based on the customer's or other's circumstances. Determination of the suitability and fitness of the product for any particular application is the sole responsibility of the purchaser of the product. This information is solely intended for informational purposes. This material confirmation relates solely to the product listed above and not as incorporated in any product or used in any process. Material Difference Technology makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose. The customer or other user of the product assumes all risk and liability arising out of the use of the product, whether used alone or in combination with other materials. The presence absence or lack of information herein with respect to any particular international, national, federal, state or local law, statute, regulation, order or rule should not be construed to mean that product is regulated under, complies with or is exempt from such international, national, federal state or local law, statute, regulation, order or rule.