

## TechResin<sup>®</sup> 2204

### ***High Density Polyethylene High Molecular Weight (HDPE-HMW) Bimodal Resin Designed For Thin Gauge Film Extrusion Applications***

TechResin<sup>®</sup> 2204 is a high molecular weight grade of HDPE designed for high drawdown to produce thin films with good processing and physical properties. TechResin<sup>®</sup> 2204 is well balanced in overall physical properties and provides good stiffness for thin gauge film applications.

TechResin<sup>®</sup> 2204 meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

#### **Suggested Applications:**

T-Shirt Bags	Multi-Wall Bag Liners
Trash Can Liners and Heavy Duty Bags	Merchandise Bags

#### **Nominal Physical Properties:**

PROPERTY	ASTM TEST METHOD	UNIT	VALUE
<b><i>Typical Resin Properties for 2204:</i></b>			
Melt Index	D1238	g/10 min.	0.04
HLMI	D1238	g/10 min.	8.50
Density	D1505	g/cm <sup>3</sup>	0.949
Melting Point	DSC	°C	131.0
<b><i>Typical 2204 Film Properties:</i></b>			
Dart Drop Impact Strength	D1709	g/mil	590
Elmendorf Tear Strength	D1922	g/mil	17/210*
Tensile Strength at Break	D882	psi.	9,800/7,000*
Tensile Elongation at Break	D882	%	290/480*
1% Secant Modulus	D882	psi.	74,000/128,000*

\* MD / TD

Note: Film properties are not intended to be used as specifications. They represent 0.50 mil film produced in laboratory conditions at a blow-up ratio of 4.0:1 and a stalk height of 8 times the die diameter. Output: 14.5 Lbs/Hr./In. Die Circumference.

*Published 02/01/12, Revised 11/10/16*

MDT does not guarantee reproduction of these results. This is not a Certificate of Analysis and the customer is responsible for testing and confirming the Material Properties before making commercial use of the product to ensure that the product is fit for the intended application and that the product can be used, and any waste material disposed of, safely, properly, and legally based on the customer's or other's circumstances. Determination of the suitability and fitness of the product for any particular application is the sole responsibility of the purchaser of the product. This information is solely intended for informational purposes. This material confirmation relates solely to the product listed above and not as incorporated in any product or used in any process. Material Difference Technology makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose. The customer or other user of the product assumes all risk and liability arising out of the use of the product, whether used alone or in combination with other materials. The presence absence or lack of information herein with respect to any particular international, national, federal, state or local law, statute, regulation, order or rule should not be construed to mean that product is regulated under, complies with or is exempt from such international, national, federal state or local law, statute, regulation, order or rule.