TechResin® B2365F

A Homopolymer High Density Polyethylene (HDPE) Resin Designed for Liquid Food Blow Molding Applications Requiring a Synthetic Antistatic Additive

TechResin® B2365F is a high quality product for those critical food packaging requirements. It also has good stiffness properties and contains a antistatic additive to help dissipate dust particles on bottle surfaces.

TechResin® B2365F meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

Suggested Applications:

Milk	Soft Drink Concentrate
Distilled Water	Fruit Juice, etc.

Nominal Physical Properties:

PROPERTY*	ASTM TEST METHOD	ENGLISH Unit	ENGLISH Value	SI Unit	SI Value
Density	D1505	g/cc	0.964	g/cc	0.964
Melt Index, Condition E, 190°C/2.16 kg	D1238	g/10 min.	0.70	g/10 min.	0.70
Environmental Stress Crack Resistance (ESCR)					
Condition B, F_{50} (100% Igepal)	D1693	h	15-20	h	15 –20
Tensile Yield Strength, 2” (50 mm) per min.	D638 Type IV	psi.	4400	MPa	30
Ultimate Elongation, 2” (50 mm) per min.	D638 Type IV	%	>300	%	>300
Brittleness Temperature	D746	°F	<-180	°C	<-118
Flexural Modulus	D790	psi.	240,000	MPa	1654

* Physical properties reported herein were determined on compression molded specimens prepared in accordance with Procedure C of ASTM D1928.

The nominal properties reported herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purposes.

Published 6/01/12, Revised 1/04/16

MDT does not guarantee reproduction of these results. This is not a Certificate of Analysis and the customer is responsible for testing and confirming the Material Properties before making commercial use of the product to ensure that the product is fit for the intended application and that the product can be used, and any waste material disposed of, safely, properly, and legally based on the customer's or other's circumstances. Determination of the suitability and fitness of the product for any particular application is the sole responsibility of the purchaser of the product. This information is solely intended for informational purposes. This material confirmation relates solely to the product listed above and not as incorporated in any product or used in any process. Material Difference Technology makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties and conditions of quality, merchanitbility and suitability or fitness for a particular purpose. the customer or other user of the product assumes all risk and liability arising out of the use of the product, whether used alone or in combination with other materials The presence absence or lack of information herein with respect to any particular international, national, federal, state or local law, statute, regulation, order or rule should not be construed to mean that product is regulated under, complies with or is exempt from such international, national, federal state or local law, statute, regulation, order or rule

Material Difference Technologies 1501 Sarasota Center Blvd, Sarasota, FL 34240
TEL: (248) 837-5501 FAX: (888) 814-9829